

## Influence of heat input on corrosion resistance of SAW welded duplex joints

J. Nowacki\*, P. Rybicki

Institute of Materials Science and Engineering, Szczecin University of Technology,  
Al. Piastow 19, 70 - 310 Szczecin, Poland

\* Corresponding author: E-mail address: jnowacki@ps.pl

Received 15.03.2006; accepted in revised form 30.04.2006

### Materials

#### ABSTRACT

**Purpose:** Purpose of this paper is description of influence of the heat input of submerged arc welding (SAW) of duplex steel UNS S31803 on welded butt joints corrosion resistance.

**Design/methodology/approach:** Butt joints on plates of 9 – 30 mm thickness were executed where the applied heat input of welding exceeded the 2.5 kJ/mm value. Maximum heat input level was  $HI \leq 3.0$ ;  $HI \leq 3.5$ ;  $HI \leq 4.0$ ;  $HI \leq 4.5$ ;  $HI \leq 5.0$ . Analysis of welding heat input influence on mechanical properties, value of ferrite share, and corrosion of test joints has been done. Non-destructive and destructive testing, e. g. visual examinations, microstructure examination, corrosion resistance tests according to ASTM G48 Method A, HV5 hardness tests, impact and tensile test were carried out. For analysis of welding heat input influence on creation of welding imperfections, there were executed welding of sheet of thickness 9, 14, 28 mm.

**Findings:** It was shown that submerged arc welding of duplex steel with the heat input from 2.5 kJ/mm up to 5.0 kJ/mm has no negative influence on properties of the joints. Based on the performed tests the conclusion is that according to DNV Rules the welding heat input exceeding the recommended values has no negative impact on strength properties and corrosion resistance of the executed welded joints.

**Research limitations/implications:** Research implications the welding heat input exceeding the recommended values should influenced the precipitation processes in the HAZ, what need further experiments.

**Practical implications:** Application of high value of the welding heat input will be profitable in terms of the welding costs.

**Originality/value:** An original value of the paper is to prove that a usage of high value welding heat input provides the best joints quality.

**Keywords:** Metallic alloys; Corrosion; Metallography; Technological design; Welding

### 1. Introduction

The heat input of submerged arc welding of steels is usually limited. High-strength steels, austenitic steels, austenitic-ferritic steels require such selection of the welding limited heat, which is a compromise between welding efficiency and joint quality [1 - 4]. Basic parameters of submerged arc welding are: arc current kind, intensity, voltage, speed of welding, wire diameter, length of wire extension, thickness and width of welding flux layer and inclination angle of an electrode or a welded joint. Welded joints of duplex austenitic-ferritic steel grades as per the Det Norske Veritas rules have to

comply with such strength criteria as bend test, impact test, tensile test, hardness test, macroscopic and microscopic examination of the executed welded joint structure, specifying percentage index of ferrite content (ferrite share), as well as performing of the welded joint corrosion resistance test.

Submerged Arc Welding (SAW) of steel grades demanding use of limited welding heat input, inclusive of high-strength steel, austenitic steels and duplex type austenitic-ferritic steels requires such selection of parameters which are a compromise between welding efficiency and joint quality [5 - 9].

When executing welded joints with a concrete kind of edge preparation for welding such optimum parameters of submerged arc

welding are specified as arc current kind, intensity, and voltage as well as speed of welding for a selected flux cored wire diameter. The quality of the weld bead is evaluated on the basis of the weld face appearance and the character of slag removal. Selection of welding parameters is intended for ensuring high operating properties of the joint, low filler metal consumption and repeatability of quality of the welds at an acceptable level. Heat input of welding is the resultant parameter that, apart from impact on technological characteristics of the welded joint has also a considerable influence on the extent of welding technology acceptance. The value of welding heat input calculated as per formula (1) may vary within  $\pm 15\%$  range of the welding heat input value applied at performing welding technology acceptance tests, observing constant parameters of the welded joint geometry [10 - 11].

The aspect of limiting the welding heat input when executing duplex steel UNS S31803 joints, frequently emphasized, keeps giving raise to controversy as regards its permissible value limit. For this purpose an attempt was made to specify the maximum heat input (HI) value of welding at which it is possible to execute the welded joint and to analyse the obtained mechanical (strength) parameters according to Det Norske Veritas Rules.

## 2. Experiment

In order to compare requirements applicable to welded joint specified in the Det Norske Veritas Rules and the impact of the welding heat input occurring at SAW welding of duplex steel UNS S31803 on the corrosion resistance of welded joints, a number of tests were performed for specifying maximum value of the welding heat input at which the welded joint loses its corrosion resistance or strength (mechanical) properties.

In connection with the above mentioned a series of butt joints on plates of 30 mm thickness were executed where the applied heat input of welding exceeded the 2,5 kJ/mm value. Beads of butt joints with butt weld were made using maximum value of welding heat input, starting from 3.0 kJ/mm and increasing every 0.5 kJ/mm up to value 5kJ / mm, in flat welding position. All welds were tested for corrosion resistance and the weld metal microstructure analysis was performed, as well as ferrite fraction was determined.

In addition, destructive and non-destructive testing of butt joints with butt-welded was performed, with heat input of welding exceeding the recommended value 2.5kJ/mm. In order to determine the influence of the multiple-pass welding/bead welding on the ferrite fraction, and on the corrosion resistance, welded joints of various thicknesses bevel pate thickness 9, 14, 28mm and with constant value of welding heat input on level 1.35kJ/mm were executed, in which filler pass and final layers were made by submerged arc welding in horizontal-vertical position. All butt weld joints were tested for corrosion resistance and the weld metal microstructure analysis was performed, as well as ferrite fraction t was determined.

The duplex steel UNS S31803 used for testing was characterized by similar chemical composition and strength parameters as given in Table 1 and the structure as on Fig. 1. Filler metal used for welding of test joints: flux cored wire of 3.2 mm diameter, grade 2205, made by Avesta Company, with the flux 805, whose strength parameters and chemical composition are given in Table 2.

Table 1.

Results of the test of chemical composition and mechanical properties of the parent material used in the experiment

Chemical composition of the steel UNS S31803, average values [%]									
C	Si	Mn	P	S	Cr	Ni	Mo	N	PREN*
0.03	0.9	1.8	0.025	0.015	22.1	5.2	2.9	0.17	$\geq 34$

Mechanical properties, average values

Re [N/mm <sup>2</sup> ]	Rm [N/mm <sup>2</sup> ]	KV -20°C [J]
590	780	170

\*PREN: Pitting Resistance Equivalent Number; PREN = 3.3 Cr [%] + Mo [%] + 16 N [%]; PREN minimal value, required according to international standards for planned constructions of chemical tankers is 34.

Table 2.

Catalogue chemical composition and mechanical properties of the filler materials - welding wire2205/flux 805 [10]

Chemical composition, average values [%]					
C	Si	Mn	Cr	Ni	Mo
0.02	0.6	1.1	23.0	8.5	3.0

Mechanical properties, average values

Re [N/mm <sup>2</sup> ]	Rm [N/mm <sup>2</sup> ]	A5 [%]	KV +20°C [J]	KV -40°C [J]
590	800	28	90	70

All butt joints with butt weld were subjected to the following non-destructive testing:

- visual examinations according to the required quality level B acc. to the Polish – European Standards PN-EN 25817,
- X-Ray examinations acc. to the Polish – European Standard PN-EN 12062 with the required quality level B as per the Polish – European Standard PN-EN 25817.




Fig. 1. Microstructure of the parent material, steel UNS S31803 used in the experiment; ferrite - dark phase, austenite - bright phase; ferrite ( $\alpha$ ) volume fraction 48%

The following destructive testing of joints were done too:

- bend test of face from the first and second side of welding at a criterion in specified bend angle 120°; mandrel diameter 5 x thickness of the test plate,
- impact test- min KV = 27J w -20 °C,
- tensile test, – min Rm = 620 MPa,
- corrosion resistance tests were carried out according to ASTM G48 Method A test and guidelines of Det Norske Veritas and American Bureau of Shipping. The specimens (76×24×16.5)

were dipped in ferric chloride reagent (100g FeCl<sub>3</sub>·6H<sub>2</sub>O in 900 ml H<sub>2</sub>O). Etching was performed at temperature 295 ± 2 K. The test duration was 24 hours. According to guidelines of Det Norske Veritas and American Bureau of Shipping the specimen mass loss smaller than 20 mg is acceptable,

- microstructure examination and ferrite share determination were performed using optical microscopy. Colour etching by Murakami's reagent (KOH – 10g; K<sub>3</sub>Fe(CN)<sub>6</sub> – 10g; H<sub>2</sub>O – 100ml) was used to produce contrast between the primary phases (ferrite and austenite) and to reveal the presence of secondary phases precipitates. A programme for analysing digital images VISILOG 4 determined the ferrite and secondary phases content. Hardness tests HV5 were performed according to EN 288 in the cross section of the welded joints in the heat-affected zone area. Six measurement points have been chosen in the face of the weld line, and the root of weld line. More detailed studies of the hardness alternation were performed using Vickers HV0.02 method. Thirty measurements of each phase in different the heat-affected zone areas (face, root) of the samples, and in different aging conditions were performed.
- macroscopic examination.

### 3. Results

Butt joints with butt weld of test plates were welded using maximum heat input at a level of HI ≤ 3.0; HI ≤ 3.5; HI ≤ 4.0; HI ≤ 4.5; HI ≤ 5.0. The X-Ray examinations of butt welded joints were performed acc. to the European standard EN12062 with the required quality level B as per EN 25817 standard (positive test results).

The destructive testing were performed as per DNV Rules. The performed bend test of face from the first and second side of welding: (min specified bend angle 120°; mandrel diameter 5 x thickness of the test plate, were positive. The metallographic examination shown ferritic – austenitic structure of the welds and HAZ and an appearance of secondary austenite in some tested joints (Fig. 2 – 4).




Fig. 2. Microstructure of the HAZ; heat input HI = 4.5; ferrite - dark phase, austenite - bright phase; ferrite (α) volume fraction 57%

The result of ferrite fraction tests, shown on Fig. 5 - 6 corresponded the acceptance level acc. to DNV rules. A tensile test of the joints was in all cases higher, than 620 MPa - required minimum value. Charpy V-notch specimens (Fig. 7) and hardness tests Vickers method – results were tests results were positive and the fracture images of welds and HAZ were ductile. Results of the corrosion resistance tests are presented in Tab. 3 and 4. Test samples subjected to corrosion resistance testing were free of any corrosion traces.




Fig. 3. Microstructure of the weld; heat input HI = 4.5; ferrite - dark phase, austenite - bright phase; ferrite (α) volume fraction 47%




Fig. 4. Diffraction image of the weld, heat input: a - HI = 3.0; kJ/mm, b - HI = 4.5; kJ/mm; αFe – ferrite, γFe - austenite




Fig. 5. Average values of ferrite volume fraction FF% in butt joints with butt welds [%]




Fig. 6. Average value of Average values of ferrite volume fraction FF% in butt joints with butt weld in the plate thickness - d function, heat input HI = 4.5 kJ/mm




Fig. 7. Average value of KV J of butt joints with butt welds (min KV = 27J at -20°C)




Figure 8. Average values of HV5 hardness of butt joints with butt welds

Table 3.

Average value of mass loss of butt-welded joints after corrosion resistance testing, plate thickness 14 mm

Max. hit input [kJ/mm]	Average value of mass loss of butt-welded joints after corrosion resistance testing [mg]
3.0	1.15
3.5	1.12
4.0	1.10
4.5	1.07
5.0	1.05

Table 4.

Average value of mass loss of butt-welded joints after corrosion resistance testing, Max. hit input 3.5 kJ/mm

Plate thickness [mm]	Average value of mass loss of butt-welded joints after corrosion resistance testing [mg]
9	1.02
14	1.12
28	1.25

## 4. Conclusions

Based on the performed tests it was proved that the welding heat input exceeding the recommended values had no negative impact on strength properties and corrosion resistance of the executed welded joints, as:

- the obtained results of strength testing of butt-welded joints, with applied heat input ranging from 3 to 5 kJ/mm are at an acceptable level with considerable strength margin,

- the performed microstructure butt joints with butt weld examination at x 400 enlargement proved that there were no intermetallic and carbides phase release, including sigma phase, the performed microstructure tee joints with butt weld examination at x 400 magnification whereas at multiple-pass welding of joints with constant heat input applied in some test pieces appeared release of secondary austenite in the weld area,
- the corrosion resistance test of the test butt joints with butt weld yielded positive result without any corrosion pits, and the tested joints mass decrement is at a level 1.25 mg, the performed corrosion resistance tests tee joints with butt weld did not show any corrosion traces (pits), whereas loss in mass was lower in 28 mm thick tested plate than in case of tested thinner plates using the same heat input of welding,
- average value of ferrite share, especially in heat affected zone (HAZ) of the welded joint was smaller than 70% level what in each of the variants complies with criteria specified both in the DNV rules, and in the references, welding of butt joints, using constant heat input, of both 9, 14 and 28mm thick plates gives comparable values of ferrite share in the executed welded joints.

## Acknowledgements

The authors would like to thank The Ministry of Education and Science of the Republic of Poland for financial support of the investigation within of the project No. 4 T08C 026 25

## References

- E. Engindeniz, Unterpulver-Hochleistungsschweißen mit Fülldrahtelektroden – materials with High Conference of Welding Technique – Essen 15-17.09.1993, Conf. Proc. 170-176.
- J. O. Nilsson; Super duplex stainless steels. Materials Science and Technology, Vol. 8 (1992), 685 - 690.
- Bernasovský, J. Orszáková, T. Žáček, J. Kudlička: The effect of welding and repairs on the properties of duplex stainless steel, Welding 5/1995. 3 - 6.
- PN-EN 28402 – Quality – Terminology, Polish – European Standard, 2001.
- J. R. Still, The use of duplex stainless steel in the offshore oil and gas industry Welding & Metal Fabrication, Aug/Sept 1994., 331 335.
- U. Draugelates, C. Bopper, A. Scharm, Properties of welded joints in ferritic-austenitic duplex, Casting, Welding and Cutting, 11/1994 E184.
- Handbook for the Welding of Stainless Steels – Catalogue Avesta Welding, 2000.
- Catalogue Elga Welding Stainless Steels – Technical Handbook 2001.
- J. O. Nilsson, T. Huhtala, P. Jonsson, L. Karlsson, A. Wilson, Structural stability of super duplex stainless wells metals and its dependence on tungsten and copper, Metallurgical and Materials Transactions A, Vol. 27A (1996), 2196 - 2200.
- J. Nowacki, Duplex – steel welding problems in the building of chemical cargo ships, Welding International, Vol. 18. No. 7 (2004) 509 – 515.
- A. Łukojć, J. Nowacki, Influence of Thermal Cycle on Structure and Properties of a Heat Affected Zone of Duplex Steels Welded Joint, Acta Metalurgica Slovaca, 1 (2004), 741 – 744.